

TECHNICAL DATA SHEET

11 19.02.2016

ANTISTAIN AQUA 2901-52

Primer for flow coating / dipping

Page 1 of 2

ANTISTAIN AQUA 2901, a water borne industrial primer for new wood designated for exterior use such as windows and doors.

ANTISTAIN AQUA 2901 reduces surface discoloration caused by tannins in hardwood.

TECHNICAL DATA

Binder: Synthetic binder

Solid content: Approx. 50 % w/w

Viscosity: 12-15 s in DIN cup 4 mm at 20 °C

60-70 s in ISO-cup 3/ 20 °C

Volatile organic compound

(VOC): See Safety Data Sheet.

Theoretical consumption: 6-8 m²/l

May vary according to wood quality and application method

Colour range: White and Antique white

APPLICATION DETAILS

Pre-treatment: The wood must be clean and free from wood dust and contamination. The moisture content of

the wood should be approx. 13 % and should not exceed 15 %.

All softwood and non-durable hardwood for exterior use should either be vacuum impregnated

(only softwood) or treated with a wood preservative.

Application: To be applied by flow coating or dipping. Due to evaporation, the solid content of the liquid must

be adjusted with water regularly.

Application conditions: The product is delivered ready for use, but can be diluted with water. Stir the product well before

use.

Film thickness – achieved by 2 x flow coat: 125-175 µm wet Optimum temperature for products and surroundings: 15-35 °C

Optimum relative air humidity: Approx. 40-80 %

System treatment: Primed parts must always be protected with a topcoat treatment before they are exposed to the

influence of the weather.

Drying times: Determined at 15-35 °C and 40-80 % relative humidity:

Dry to handle: 1-2 hours
Dry to sand* / dry to recoat: 2-3 hours

*As the layer thickness is of paramount importance for the effectiveness of the product, it is

important not to sand the surface too much. This also counts if diluted.

Industrial Wood www.teknos.com



TECHNICAL DATA SHEET

11 19.02.2016

Page 2 of 2

ANTISTAIN AQUA 2901-52

The drying time can be reduced using special drying systems to force drying. The drying times are approximate and may vary according to wood quality, temperatures, humidity, ventilation and

film thickness.

Cleaning: The equipment is cleaned with water.

HEALTH AND SAFETY See Safety Data Sheet.

ADDITIONAL INFORMATION

Pack size: 3, 10, 20, 120 and 1,000 l

Storage: The product must be stored at temperatures above 5 °C. Shelf life in unopened containers: See

"Best before date" on the label. Keep containers tightly closed after use.

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets are available from our homepage www.teknos.com.

Industrial Wood www.teknos.com