











Overview

Main Benefits

- Excellent chemical resistance
- High impact strength
- Easily fabricated and formed
- Highest fire rating, self-extinguishing
- Glossy, Matte Hair-Cell or surfaces
- High electrical and thermal insulation
- Easy fabrication
- Non toxic
- PALOPAQUE HYG: Active hygiene

- Wall cladding
- Signs, displays and point of purchase

Typical Applications

- Chemical process industries
- Chemically resistant signs
- Sterile surfaces in laboratories
- Clinics and hospitals
- Food industry
- Air vents





Build On.

www.palram.com

Colors

STD White	Off White	Light Pistachio	Cream	Stone	
		Deep Ice	Light Pink	Lilac	
Red Wine	Dark Pink	Red	Orange	Crimson Pink	
Avocado	Green Grape	Limba Dlum		0 01	
	Green Grape	Light Blue	Light Turquoise	Ocean Blue	
Mouse Grey	Medium Grey	Black	Dark Grey	Light Grey	

^{*} Color may vary slightly with different surface finishes.

Surface Finishes

PALOPAQUE is offered with glossy smooth finish on both sides as standard. Matte and Hair-Cell finishes on one side are optional.

Standard Dimensions

Width x Length (mm)	Thickness (mm)
1220 x 2440	1 to 15
1000 x 2000	1 to 10
1500 x 3000	1 to 6
2000 x 3000	1 to 4

^{*} Custom dimensions are available, subject to minimum quantity.

PALOPAQUE™ Product Range

Type	Description
PALOPAQUE™	Standard UV stabilized sheet for general purpose and thermoforming applications. *Increased UV resistance is available upon special request
PALOPAQUE™ HYG	Hygienic panels with active antimicrobial action, effectively eliminating a wide range of harmful microbes.

Fabrication Tips

Typical Physical Properties

Property	Method*	Conditions	Units	Value
Density	D-792		g/cm³	1.4
Heat deflection temperature (H.D.	T) D-648	Load: 1.82MPa	°C	65 - 68
Service Temperature			°C	-10 to +50
Thermal conductivity	C-177		W/m K	0.15
Coefficient of linear thermal expar	nsion D-696		cm/cm °C	6.7 x 10 ⁻⁵
Rockwell hardness	D-785		R Scale	97R
Tensile strength at yield	D-638	10 mm/min	MPa	50
Tensile strength at break	D-638	10 mm/min	MPa	45
Elongation at yield	D-638	10 mm/min	%	3
Elongation at break	D-638	10 mm/min	%	>80
Tensile modulus of elasticity	D-638	1 mm/min	MPa	2,900
Flexural strength	D-790	1.3 mm/min	MPa	80
Flexural modulus	D-790	1.3 mm/min	MPa	2,700
Impact falling weight ISC	O 6603/1 E ₅₀	3 mm sheet	J	95

^{*} ASTM except where noted otherwise

Resistance to Chemicals

Excellent resistance to... Mineral acids, alkalis, plating solutions, paper making chemicals, pickling solutions, other inorganic solutions and fumes thereof.

Good resistance to... Alcohols, aliphatic hydrocarbons, glycols, amines, phenols.

Not recommended to contact... ketones, chlorinated solvents, aromatic hydrocarbons, some esters and ethers.

Flammability

PALOPAQUE is self-extinguishing and complies with the most demanding international fire resistance standards defined in the field of plastics, as shown in the attached table.

Product	Standard	Classification
	EN 13501	B, s3, d0
PALOPAQUE™	BS 476/7	Class 0
	ASTM E 84	Class A
PALOPAQUE™ LS (Low Smoke)	EN 13501	B, s2, d0

PALOPAQUE can be easily fabricated using various techniques. Below are general recommendations for some of them.

Sawing	Machining	Thermoforming	Drilling	Bonding	Welding
	speeds for turning and shaping, and assure free removal of	Between 130°C and 170°C PALOPAQUE sheets become formable and can then be formed, press molded or blow formed.	Use conventional drills, but be certain to remove free drill chips in order to avoid overheating of the sheet. Also, use slow rate of penetration.	can be bonded with conventional solvent	PALOPAQUE extruded PVC sheets can be welded by hot-air welding process conventionally used for PVC.



PALRAM NSW

196 Newton Road Wetherill Park, NSW 2164 Ph: 02-9757 3166 new.south.wales@palram.com victoria@palram.com

PALRAM VIC

16 Merri Concourse Campbellfield, VIC 3061 Ph: 03-9357 9240

PALRAM SA

517a Cross Keys Road Cavan SA 5094 Ph: 08-82622288 $south. australia@palram.com \\ western. australia@palram.com \\ queens land@palram.com \\$

PALRAM WA

74 Christable Wav Landsdale WA 6065 Ph: 08-9302 4173

PALRAM QLD

Unit 9C, 380 Bilsen Rd Geebung QLD 4034 Ph: 07-3172 5581



n as much as Palram Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any Palram Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. Palram Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local Palram Industries supplier to ensure that you have obtained the most up to date information.













^{*}For more information please refer to "Chemical Resistance of PVC Products" available at www.palram.com or with your PALRAM distributor.