



# SUNSKY® Trimdeck Premium

Longer Span - Stronger impact - More Light



## Overview

SUNSKY® Trimdeck contribute to the conservation of energy and improve the quality of the working environment. They stand up to demanding exterior usage and offer multiple advantages over alternatives.

SUNSKY® Trimdeck are designed for use as in-plane rooflights and sidelights with profiled metal roofs. Advanced profile matching technology enables integration with virtually any metal profile.

SUNSKY® panels form a complete shield against harmful UV rays while admitting most of the visible light. Clear panels allow maximum light in, while a range of colors and diffusions offer various solar transmission options and reduced heat loads.

## Main Benefits

- 1.25mm thickness
- Virtually unbreakable
- Self extinguishing
- Maintains high light transmission far better than alternative materials
- Wide service temperature range (-50°C to 120°C)
- Easily and safely installed
- Ten year warranty
- Hail and wind resistant
- Filters over 99% of UV radiation

## Typical Applications

- Skylights for metal roofs
- Sidelights for metal walls

Load (kpa)	End Span	Mid Span
1.00	1350	1800
1.25	1275	1700
1.50	1200	1600
1.75	1125	1500

Tested to AS/NZS 4040.4-2006 (sandbag test) to the requirements of AS 1562.3 2006



## SUNSKY® Trimdeck Premium

1.25mm thick Skylight application



[www.palram.com.au](http://www.palram.com.au)



# SUNSKY® Trimdeck Premium

## Colours\*

Colour/Type	%LT	%Haze	Colour/Type	%LT	%Haze
Clear	90	<1	Diffuser	85	100
White Opal	35	100	Diffused Ice	25	100


\* Light transmission data conforms to ASTM D-1003 standard

## Systems and Accessories

Self drill screw 65mmX14g



Top & Bottom Foam Infills



Butyl Rubber



Cyclon washer with EPDM gasket



Stitching Screws (Grommet seals) with EPDM seal



Stitching screws 6.35mm x 19mm (¼" x ¾")  
self-tapping screw with 19mm washer



Clearfix screw



## SUNSKY® Product Range

Product	Description
SUNSKY® 1001	Corrugated polycarbonate sheet within a low range of colours
SUNSKY® UV2	With UV protection on both sides
SUNSKY® Embossed	Embossed or Hair Cell finish on one sides
SUNSKY® Plus	For greenhouse covering, with anti-condensation treatment
SUNSKY® 2001	Corrugated polycarbonate sheet with extra UV protection on one side
SUNSKY® 3001	Advanced heat blocking with high clarity

## Visit [www.PALRAM.com.au](http://www.PALRAM.com.au)

To learn more about SUNSKY® Skylights and other Palram products, please visit [www.palram.com.au](http://www.palram.com.au)



**PALRAM SA/NT**  
517A Cross keys Road  
Cavan SA 5094  
Tel: (08) 8262 2288  
Fax: (08) 8262 3388  
salesa@palram.com.au

**PALRAM NSW/ACT**  
1 Cox Place Glendenning  
NSW 2761  
Tel: (02) 9757 3166  
Fax: (02) 9756 1008  
salesnsw@palram.com.au

**PALRAM QLD**  
Unit 9C / 380 Bilsen Road  
Geebung QLD 4034  
Tel: (07) 3172 5581  
Fax: (07) 3172 5516  
salesqld@palram.com.au

**PALRAM VIC/TAS**  
34 Buys Court Derrimut  
VIC 3030  
Tel: (03) 9357 9240  
Fax: (03) 9357 9270  
salesvic@palram.com.au

**PALRAM WA**  
74 Christable Way  
Landsdale WA 6065  
Tel: (08) 9302 4173  
Fax: (08) 9302 5287  
saleswa@palram.com.au

68623 - 08.2012

In as much as PALRAM Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any PALRAM Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. PALRAM Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local PALRAM Industries supplier to ensure that you have obtained the most up to date information.

©1997 PALRAM Industries Ltd. | SUNSKY is a registered trademark of PALRAM Industries Ltd.

## Typical Physical Properties

Property	Method*	Conditions	Units	Value
Density	D-792		g/cm <sup>3</sup>	1.2
Heat deflection temperature (H.D.T)	D-648	Load: 1.82 MPa	°C	135
Service Temperature Range (Short term)			°C	-50 to +120
Service Temperature Range (Long term)			°C	-50 to +100
Coefficient of linear thermal expansion	D-696		cm/cm°C	6.5 x 10 <sup>-5</sup>
Thermal conductivity	C-177		W/m K	0.21
Tensile strength at yield	D-638	10 mm/min	MPa	62
Tensile strength at break	D-638	1 mm/min	MPa	65
Elongation at yield	D-638	10 mm/min	%	6
Elongation at break	D-638	10 mm/min	%	>70
Tensile modulus of elasticity	D-638	1 mm/min	MPa	2,300
Flexural strength mechanical	D-790	1 mm/min	MPa	93
Flexural modulus	D-790	1.3 mm/min	MPa	1,890
Rockwell hardness	D-785		R Scale	118
Light transmission	D-1003	Clear sheet	%	90%
Haze	D-1003	Clear sheet	%	<0.5
Yellowness index	D-1003	Clear sheet	YI	<1

\* ASTM method except where noted otherwise

## Flammability

SUNSKY® has a low flammability rating and does not emit toxic gasses when burning.

Standard	Classification*
EN13501	B, s1, d0
NFP 92501, 4, 5	M-1
DIN 4102	B-1
UL 723	4.7, 47.0
Los Angeles Building Code	CC2 (Section 2603)
UNI 9177, 9176	Class 2

\* For additional information please contact your PALRAM distributor

## UV Blocking and Resistance

SUNSKY® transmits radiation selectively and completely shield against harmful UV (ultraviolet) rays. SUNSKY itself withstands the detrimental effects of UV radiation, as specified in the SUNSKY warranty.

